




### Non-ambient attachment for XRD

## HTK 2000N – high-temperature chamber

#### **Benefits**

- In situ powder X-ray diffraction studies for temperatures up to 2300 °C
- Allows for extremely fast heating rates
- Chamber design optimized for a minimum temperature gradient along the heating strip and maximum position stability of the sample
- Integrated alignment slits allow exact positioning of the strip surface even at high temperatures
- A choice of heating strips depending on experimental requirements
- Easy access to the heating strip for straightforward sample preparation

#### Application example




Formation of Mg-Al Spinel from mixture of Corundum and Periclase

# HTK 2000N chamber




#### **Features**



25-2300 °C (tungsten strip) 25-1600 °C (platinum strip) 25-1500 °C (tantalum strip) Max. heating rate: 900 °C/min Recommended heating rate: 600 °C/min


Direct heating



Air

Vacuum 10<sup>-4</sup> mbar Inert gases

Atmospheres



Flat plate reflection geometry.

#### **Platinum**

air, vacuum, inert gas

#### Tungsten

vacuum

#### Tantalum

vacuum

#### Conclusion

The HTK 2000N high-temperature chamber is an ideal choice for *in situ* studies of phase transformations and changes of structural properties when extremely high temperatures are required.

Heating strips